


This MotoCAP safety rating applies to:

Brand: Dririder
Model: Blizzard 3
Type: Pants - Textile
Date purchased: 13 May 2019
Sizes tested: 2XL,
Gender: M & F
Style: All Purpose
Test code: P19T03


Test Results Summary:

	Rating	Score
MotoCAP Protection Rating	★	16.0
Abrasion	1/10	0.65
Burst	10/10	1276
Impact	0/10	0.0
MotoCAP Comfort Rating	★	0.16
Moisture Vapour Resistance		98.6
Thermal Resistance		0.264
Water resistance	1/10	44.6

This garment is fitted with impact protectors for the knees. There are no pockets provided at the hips for aftermarket impact protectors. There are no vents to allow airflow movement through the garment.

Jacket and Pants - Crash Impact Risk Zones

This diagram is a pictorial representation of the crash impact risk Zones.


Zone 1


High risk of abrasion
High risk of impact

Zone 2


High risk of abrasion

Zone 3


Medium risk of abrasion

Zone 4


Low risk of abrasion

Abrasion Resistance

The garment was tested for abrasion resistance in accordance with MotoCAP test protocols. The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone.

Details of materials used in garment:

- Material A: Fabric shell, fabric layer, water-resistant layer and mesh inner liner
 Material B: Fabric shell, water-resistant layer and mesh inner liner
 Material C: Elastic fabric shell, water-resistant layer and mesh inner liner

Zone	Coverage (%)	Abrasion time for each test (seconds)						Average (seconds)	
		1	2	3	4	5	6		
Zone 1 and 2 areas (High abrasion risk)									
Material A	75%	1.44	1.06	0.84	1.26	0.83	1.18	1.10	P
Material B	25%	0.62	0.54	0.47	0.62	0.57	0.49	0.55	P
Zone 3 area (Medium abrasion risk)									
Material B	100%	0.62	0.54	0.47	0.62	0.57	0.49	0.55	P
Zone 4 area (Low abrasion risk)									
Material B	50%	0.62	0.54	0.47	0.62	0.57	0.49	0.55	M
Material C	50%	0.57	0.35	0.35	0.47			0.44	M

Abrasion times are capped at a maximum of 10.00s.

The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table above. The colour coding is based on the worst performing material in each zone.



Determining Criteria		Good	Acceptable	Marginal	Poor
High abrasion risk	Zone 1/2:	> 5.6	3.0 - 5.6	1.3 - 2.9	< 1.3
Medium abrasion risk	Zone 3:	> 2.5	1.8 - 2.5	0.8 - 1.7	< 0.8
Low abrasion risk	Zone 4:	>1.5	1.0 - 1.5	0.4 - 0.9	< 0.4

Burst Strength

The garment's burst strength was tested in accordance with MotoCAP test protocols. The table below shows the burst pressure in kilopascals (kPa) for each sample tested by Zone and the average result for each zone.

Burst pressure (kPa)


Area	1	2	3	4	5	Average	
Zones 1 & 2	1361	1205	1573	939	982	1212	G
Zone EZ	1934	1386	1012	755	1702	1358	G
Zones 3 & 4	1525	864	1035	1106	1668	1239	G

The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table above.



Determining Criteria

Burst strength



Impact Protection

The garment was tested for impact protection and coverage in accordance with MotoCAP test protocols. The table below shows the test results for each strike on each impact protector in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone.

Impact protector type	Knee		Hip	
Average force (kN)	19.9	A		P
Maximum force (kN)	23.0	A		P
Coverage of zone 1 area	110%		0%	
Coverage of zone after displacement	80%		0%	

Individual test results

Impact force (kN)	Knee			Hip	No impact protector present		
	A	B	C		A	B	C
Impact Protector 1	17.9	21.5	22.5				
Impact Protector 2	17.6	21.8	23.0				
Impact Protector 3	14.1	21.4	19.5				

The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table above. The colour coding is based on the worst performing score for average or maximum force for each impact zone.



Determining Criteria

Impact force (kN)	Good	Acceptable	Marginal	Poor*
	< 15	15 - 24	25 - 30	> 30

* Poor may also indicate that no impact protector, or impact protector pocket is present in the garment

Areas shaded black are not considered in the impact protection ratings.

Thermal comfort

The garment was tested for thermal comfort following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

	1	2	Average
Moisture Vapour Resistance - R_{et} (kPam ² /W)	92.9	104.3	98.6
	1	2	Average
Thermal Resistance - R_{ct} (Km ² /W)	0.246	0.281	0.264

Water spray and rain resistance

This garment is advertised as water-resistant, and so has been tested for water spray and rain resistance according to the MotoCAP test protocols. The table below shows the water absorbed (ml) and the wetting proportion (%) of the garment and undergarments due to water absorption.

	Water absorbed by garment		Water absorbed by underwear	
	Volume (ml)	Percentage (%)	Volume (ml)	Percentage (%)
Garment 1	411	29%	6	2.4%
Garment 2	392	27%	231	86.8%
Average	268	28%	79	44.6%

Location of wetting:

Visible wetting to the cotton underwear worn under the water-resistant motorcycle garment was present on the upper and lower legs for the first test garment and over the entire garment for the second.