

MOTOCAP

This MotoCAP safety rating applies to:

Brand:	Alpinestars
Model:	Stella Andes V2 Drystar
Туре:	Pants - Textile
Date purchased:	26 August 2019
Sizes tested:	XL
Gender:	F
Style:	All Purpose
Test code:	P19T09


Test Results Summary:

	Rating	Score
MotoCAP Protection Rating	*	15.7
Abrasion	1/10	0.41
Burst	10/10	1370
Impact	1/10	0.0
MotoCAP Comfort Rating	**	0.309
Moisture Vapour Resistance		55.2
Thermal Resistance		0.285
Water resistance	9/10	1.8

This garment is fitted with impact protectors for the knees. Velcro tabs are provided at the hips for aftermarket impact protectors. There are vents in the upper legs to allow airflow movement through the garment. The thermal comfort rating is based on tests of the breathability of the garment when all vents are closed. The thermal comfort of this product may be better when the vents can be opened.

Jacket and Pants - Crash Impact Risk Zones

This diagram is a pictorial representation of the crash impact risk Zones.





Abrasion Resistance

The garment was tested for abrasion resistance in accordance with MotoCAP test protocols. The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone.


Details of materials used in garment:

Material A:	High density woven fabric shell, water-resistant layer and mesh inner liner
Material B:	Woven fabric shell, water-resistant layer and mesh inner liner

Zone	Coverage	Abrasion time for each test (seconds)						Average
	(%)	1	2	3	4	5	6	(seconds)
Zone 1 and 2	areas (High abra	asion risk)						
Material A	50%	1.21	1.03	0.87	1.28	0.99	0.96	1.06 P
Material B	50%	0.31	0.52	0.56	0.55	0.49	0.55	0.50 P
Zone 3 area (l	Medium abrasio	n risk)						
Material A	20%	1.21	1.03	0.87	1.28	0.99	0.96	1.06 M
Material B	80%	0.31	0.52	0.56	0.55	0.49	0.55	0.50 P
Zone 4 area (I	Low abrasion ris	sk)						
Material A	5%	1.21	1.03	0.87	1.28	0.99	0.96	1.06 A
Material B	95%	0.31	0.52	0.56	0.55	0.49	0.55	0.50 <mark>M</mark>

Abrasion times are capped at a maximum of 10.00s.

The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table above. The colour coding is based on the worst performing material in each zone.



High abrasion risk

Low abrasion risk




Burst Strength

The garment's burst strength was tested in accordance with MotoCAP test protocols. The table below shows the burst pressure in kilopascals (kPA) for each sample tested by Zone and the average result for each zone.

Burst pressure (kPA)							
Area	1	2	3	4	5	Average	
Zones 1 & 2	1596	1700	1054	1817	1608	1555	G
Zone EZ	1273	1405	1139	801	1262	1176	G
Zones 3 & 4	1232	1312	1247	1418	1725	1387	G

The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table above.






Impact Protection

The garment was tested for impact protection and coverage in accordance with MotoCAP test protocols. The table below shows the test results for each strike on each impact protector in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone.

Impact protector type		Knee			Hip	
Average force (kN)		20.7	A			Ρ
Maximum force (kN)		24.0	A			Р
Coverage of zone 1 area		90%			0%	
Coverage of zone after di	splacement	90%			0%	
Individual test results						
Impact force (kN)	Knee			Hip	No impact prote	ector present
Strike location	Α	В	С	Α	В	С
Impact Protector 1	21.7	19.0	24.0			
Impact Protector 2	19.4	23.1	18.6			
Impact Protector 3	18.6	20.3	21.9			

The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table above. The colour coding is based on the worst performing score for average or maximium force for each impact zone.



* Poor may also indicate that no impact protector, or impact protector pocket is present in the garment

Areas shaded black are not considered in the impact protection ratings.

Impact force



Thermal comfort

The garment was tested for thermal comfort following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

	1	2	Average
Moisture Vapour Resistance - R _{et}	62.9	47.4	55.2
(kPam²/W)			
	1	2	Average
Thermal Resistance - R _{ct}	0.284	0.285	0.285

Water spray and rain resistance

This garment is advertised as water-resistant, and so has been tested for water spray and rain resistance according to the MotoCAP test protocols. The table below shows the water absorbed (ml) and the wetting proportion (%) of the garment and undergarments due to water absorption.

	Water absorbe	ed by garment	Water absorbed by underwear		
	Volume (ml) Percentage (%)		Volume (ml)	Percentage (%)	
Garment 1	138	14%	6.3	2.6%	
Garment 2	175	17%	2.5	1.0%	
Average	157	16%	4.4	1.8%	

Location of wetting:

There was no visible wetting to the cotton underwear worn under the motorcycle water-resistant garment.