

MOTOCAP

This MotoCAP safety rating applies to:


Brand	Rjays
Model	Samurai 3
Туре	Jacket - Leather
Date purchased	6 July 2020
Sizes tested	56 & 54
Test garment gender	Male
Style	Sports
RRP	\$699.96

Test Results Summary	Rating	Score
MotoCAP Protection Rating	***	50.8
Abrasion	7/10	5.40
Burst	10/10	1330
Impact	5/10	35.1
MotoCAP Breathability Rating	***	0.424
Moisture Vapour Resistance	-	39.7
Thermal Resistance	-	0.281
Water resistance	N/A	N/A

This garment is fitted with impact protectors for the elbows and shoulders. A pocket is provided for an aftermarket back protector. Replacing the elbow and shoulder armour with higher performing impact protectors would improve the protection levels of this garment. There are no vents to allow airflow movement through the garment.

Jacket and Pants - Crash Impact Risk Zones

This diagram is a pictorial representation of the crash impact risk Zones.





Abrasion Resistance

The jacket was tested for abrasion resistance in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table below. The colour coding is based on the worst performing material in each zone.



Abrasion Resistance Performance Abrasion rating 7/10

Abrasion rating	7/10
Abrasion score	5.40

Determining Criteria	Area	Good	Acceptable	Marginal	Poor
High abrasion risk	Zones 1 & 2	> 5.6	3.0 - 5.6	1.3 - 2.9	< 1.3
Medium abrasion risk	Zone 3	> 2.5	1.8 - 2.5	0.8 - 1.7	< 0.8
Low abrasion risk	Zone 4	>1.5	1.0 - 1.5	0.4 - 0.9	< 0.4

Individual Abrasion Resistance Results: - The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone. Abrasion times are capped at a maximum of 10.00s.

Abrasion time for each test (seconds)

Zones 1 & 2	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average
Material A	80%	6.52	6.35	7.05	5.40	5.64	5.77	6.12 G
Material B	20%	3.66	4.73	5.15	4.93	5.50	5.15	4.85 A
Zone 3	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average
Material B	100%	3.66	4.73	5.15	4.93	5.50	5.15	4.85 G
Zone 4	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average
Material B	90%	3.66	4.73	5.15	4.93	5.50	5.15	4.85 G
Material C	10%	0.67	0.39	0.39				0.48 M

Details of materials used in jacket

Material A	Leather shell, foam layer and mesh inner liner
Material B	Leather shell with mesh inner liner
Material C	Stretch fabric shell with mesh inner liner



Burst Strength

The jacket was tested for burst strength in accordance with MotoCAP test protocols. The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table below.



Burst Strength Performance				
Burst rating	10/10			
Burst score	1330			

Determining Criteria	Unit	Good	Acceptable	Marginal	Poor
Burst strength	(kPa)	> 1000	800 - 1000	500 - 799	< 500

Individual Burst Strength Results: - The table below shows the burst pressure in kilopascals (kPA) for each sample tested by Zone and the average result for each zone.

Burst pressure for each seam (kPA)

Area	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Zones 1 & 2	1254	1175	1823	1269	1228	1025	1296	G
Zones 3 & 4	1948	254	1946	1854	1946	841	1465	G



Impact Protection

The jacket was tested for impact protection and coverage in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table below. The colour coding is based on the worst performing score for average or maximium force for each impact zone. Areas shaded black are not considered for impact protection ratings.



Determining Criteria	Unit	Good	Acceptable	Marginal	Poor*
Impact force	(kN)	< 15	15 - 24	25 - 30	> 30

* Poor may also indicate that no impact protector, or impact protector pocket is present in the garment

Impact Protector Results: - The table below shows the average and maximum force transmitted through each impact protector type in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone.

npact protector type Elbow			Shoulder		
Average force (kN)	25.2 N	Λ	26.0	Μ	
Maximum force (kN)	32.4 F		29.6	Μ	
Coverage of Zone 1 area	150%	_	110%		
Coverage of Zone after displacement	100%		100%		

Individual Impact Protector Results: - The table below shows the test results for each strike on individual impact protectors in kilonewtons (kN) and the position of the strike. Individual strike results are capped at a maximum of 50kN.

Force transfer for each impact strike (kN)

Impact protector type	Elbow			Shoulder		
Strike location	Centre	Mid	Edge	Centre	Mid	Edge
Impact Protector 1	19.9	19.6	20.2	25.1	22.1	23.9
Impact Protector 2	27.1	26.6	21.3	28.8	24.7	25.1
Impact Protector 3	32.4	29.8	29.8	28.7	26.0	29.6



Breathability

The jacket was tested for breathability following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

Without removable liners		With water-resistant liner			
Breathability rating ★★★		Breathability rating		N/A	
Breathability score	0.424	Breathability score N/A			
Moisture Vapour Resistance - R _{et} (kPa.m ² /W)		1	2	Average	
Without removable liners		40.0	39.4	39.7	
With water-resistant liner		N/A	N/A	N/A	
Thermal Resistance - R _{ct} (K.m²/W)		1	2	Average	
Without removable liners	S	0.281	0.280	0.281	
With water-resistant liner		N/A	N/A	N/A	

Water spray and rain resistance

This jacket has not been advertised as water-resistant so has not been tested for water spray and rain resistance.

Assessment Details.

Brand	Rjays		
Model	Samurai 3		
Туре	Jacket - Leather		
Date purchased	6 July 2020		
Tested by	AMCAF, Deakin University		
Garment test reference	J19L43		
Rating first published	November 2020		
Rating updated	24 November 2020		

