



This MotoCAP safety rating applies to:

Brand Richa

Model Brutus Gore-Tex
Type Jacket - Textile
Date purchased 5 December 2022

Sizes tested L and 3XL

Test garment gender Male

Style All Purpose


RRP \$1,049.00

Test Results Summary	Rating	Score
MotoCAP Protection Rating	*	25.8
Abrasion	1/10	0.61
Burst	8/10	887
Impact	6/10	46.4
MotoCAP Breathability Rating	*	0.196
Moisture Vapour Resistance	-	101.9
Thermal Resistance	-	0.333
Water resistance	2/10	23.8

This garment is fitted with impact protectors for the elbows and shoulders. Pockets are provided at chests and back for fitting aftermarket impact protectors. There are zipped vents in the upper chest, lower arms and sides of back to allow controlled airflow movement through the garment. The breathability rating is based on tests of the garment's materials when all vents are closed. The breathability of this product may be better when the vents can be opened. This garment has a removable water-resistant liner. The breathability rating above was achieved with the thermal and water-resistant liners removed. When tested with the water-resistant liner installed, the breathability rating reduced to half a star.

Jacket and Pants - Crash Impact Risk Zones

This diagram is a pictorial representation of the crash impact risk Zones.





Abrasion Resistance

The jacket was tested for abrasion resistance in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table below. The colour coding is based on the worst performing material in each zone.



Abrasion Resistance Performance

Abrasion rating	1/10
Abrasion score	0.61

Determining Criteria	Area	Good	Acceptable	Marginal	Poor
High abrasion risk	Zone 1 & 2	> 5.6	3.0 - 5.6	1.3 - 2.9	< 1.3
Medium abrasion risk	Zone 3	> 2.5	1.8 - 2.5	0.8 - 1.7	< 0.8
Low abrasion risk	Zone 4	>1.5	1.0 - 1.5	0.4 - 0.9	< 0.4

Individual Abrasion Resistance Results: - The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone. Abrasion times are capped at a maximum of 10.00s.

Abrasion time for each test (seconds)

oi eacii lesi (se	conusj							
Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
90%	0.66	0.65	0.79	0.70	0.67	0.58	0.67	Р
10%	0.64	0.65	0.37	0.57	0.60	0.51	0.56	Р
Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
100%	0.64	0.65	0.37	0.57	0.60	0.51	0.56	Р
Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
100%	0.64	0.65	0.37	0.57	0.60	0.51	0.56	M
	Coverage (%) 90% 10% Coverage (%) 100% Coverage (%)	Coverage (%) Sample 1 90% 0.66 10% 0.64 Coverage (%) Sample 1 100% 0.64 Coverage (%) Sample 1	Coverage (%) Sample 1 Sample 2 90% 0.66 0.65 10% 0.64 0.65 Coverage (%) Sample 1 Sample 2 100% 0.64 0.65 Coverage (%) Sample 1 Sample 2	Coverage (%) Sample 1 Sample 2 Sample 3 90% 0.66 0.65 0.79 10% 0.64 0.65 0.37 Coverage (%) Sample 1 Sample 2 Sample 3 100% 0.64 0.65 0.37 Coverage (%) Sample 1 Sample 2 Sample 3	Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 90% 0.66 0.65 0.79 0.70 10% 0.64 0.65 0.37 0.57 Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 100% 0.64 0.65 0.37 0.57 Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4	Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 Sample 5 90% 0.66 0.65 0.79 0.70 0.67 10% 0.64 0.65 0.37 0.57 0.60 Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 Sample 5 100% 0.64 0.65 0.37 0.57 0.60 Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 Sample 5	Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 Sample 5 Sample 6 90% 0.66 0.65 0.79 0.70 0.67 0.58 10% 0.64 0.65 0.37 0.57 0.60 0.51 Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 Sample 5 Sample 6 100% 0.64 0.65 0.37 0.57 0.60 0.51 Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 Sample 5 Sample 6	90% 0.66 0.65 0.79 0.70 0.67 0.58 0.67 10% 0.64 0.65 0.37 0.57 0.60 0.51 0.56 Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 Sample 5 Sample 6 Average 100% 0.64 0.65 0.37 0.57 0.60 0.51 0.56 Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 Sample 5 Sample 6 Average

Details of materials used in jacket

Material A	Coarse woven fabric shell with mesh inner liner
Material B	Woven fabric shell with mesh inner liner



Burst Strength

The jacket was tested for burst strength in accordance with MotoCAP test protocols. The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table below.



Burst Strength Performance

Burst rating	8/10
Burst score	887

Determining Criteria	Unit	Good	Acceptable	Marginal	Poor
Burst strength	(kPa)	> 1000	800 - 1000	500 - 799	< 500

Individual Burst Strength Results: - The table below shows the burst pressure in kilopascals (kPA) for each sample tested by Zone and the average result for each zone.

Burst pressure for each seam (kPA)

Area	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Zones 1 & 2	1190	707	842	1379	628	736	914	Α
Zones 3 & 4	1061	435	729	1141	720	591	779	М



Impact Protection

The jacket was tested for impact protection and coverage in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table below. The colour coding is based on the worst performing score for average or maximum force for each impact zone. Areas shaded black are not considered for impact protection ratings.



Impact Protection Performance

Impact rating 6/10 Impact score 46.4

Determining Criteria	Unit	Good	Acceptable	Marginal	Poor*
Impact force	(kN)	< 15	15 - 24	25 - 30	> 30

^{*} Poor may also indicate that no impact protector, or impact protector pocket is present in the garment

Individual Impact Protector Results: - The table below shows the test results for each strike on each impact protector in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone. Individual strike results are capped at a maximum of 50kN.

Impact protector type	Elbow		Shoulder
Average force (kN)	19.8	A	16.3 A
Maximum force (kN)	24.8	A	17.1 A
Coverage of Zone 1 area	115%		105%
Coverage of Zone after displacement	100%		100%

Individual Impact Protector Results: - The table below shows the test results for each strike on individual impact protectors in kilonewtons (kN) and the position of the strike. Individual strike results are capped at a maximum of 50kN.

Force transfer for each impact strike (kN)

Impact protector type	Elbow	Shoulder				
Strike location	Centre	Mid	Edge	Centre	Mid	Edge
Impact Protector 1	18.4	19.2	18.6	15.4	16.3	16.5
Impact Protector 2	18.6	19.0	22.7	16.4	16.0	16.9
Impact Protector 3	17.4	19.8	24.8	15.4	16.6	17.1



Breathability

The jacket was tested for breathability following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

Without removable	liners	With	n water-resista	ant liner
Breathability rating	Brea	thability rating	+	
Breathability score	0.196	Brea	thability score	0.118
Moisture Vapour Resi	stance - R _{et} (kPa.m²/W)	1	2	Average
Without removable line	rs	91.4	112.3	101.9
With water-resistant line	er	196.0	221.1	208.6
Thermal Resistance -	R _{ct} (K.m²/W)	1	2	Average
Without removable line	rs	0.333	0.334	0.333
With water-resistant line	er	0.407	0.416	0.411

Water spray and rain resistance

This jacket is advertised as water-resistant, and so has been tested for water spray and rain resistance according to the MotoCAP test protocols. The table below shows the water absorbed (ml) and the wetting proportion (%) of the garment and undergarments due to water absorption.

	Water absorbed by garment		Water absorbed by underwear	
	Volume (ml)	Percentage (%)	Volume (ml)	Percentage (%)
Jacket 1	477	27%	52	18%
Jacket 2	499	29%	81	29%
Average	488	28%	66	24%

Location of wetting

Page 5 of 5

There was major wetting to the cotton underwear present at the cuffs of the sleeves, neck and chest for one jacket tested. And there was minor wetting to the cotton underwear present at the cuffs of the sleeves, and major wetting to the neck and chest for the other jacket tested.

Assessment Details	.
Brand	Richa
Model	Brutus Gore-Tex
Туре	Jacket - Textile
Date purchased	5 December 2022
Tested by	AMCAF, Deakin University
Report approved by	MotoCAP Chief Scientist
Garment test reference	J21T19
Rating first published	February 2023
Rating updated	8 February 2023