


This MotoCAP safety rating applies to:


| | |
|---------------------|----------------------------|
| Brand | 1Tonne |
| Model | Explorer All Season Ladies |
| Type | Jacket - Textile |
| Date purchased | 22 May 2023 |
| Sizes tested | 16 and 18 |
| Test garment gender | Female |
| Style | All Purpose |
| RRP | \$199.00 |


| Test Results Summary | Rating | Score |
|------------------------------|--------|-------|
| MotoCAP Protection Rating | ★ | 20.6 |
| Abrasion | 2/10 | 1.40 |
| Burst | 9/10 | 999 |
| Impact | 2/10 | 12.0 |
| MotoCAP Breathability Rating | ✱ | 0.042 |
| Moisture Vapour Resistance | - | 482.9 |
| Thermal Resistance | - | 0.341 |
| Water resistance | 1/10 | 36.3 |


This garment is fitted with impact protectors for the elbows and shoulders. A pocket is provided for an aftermarket back protector. Replacing the elbow and shoulder armour with higher performing impact protectors would improve the protection levels of this garment. Mesh panels are located in the back and zipped vents in the chest and arms allow airflow movement through the garment. The breathability rating is based on tests of the garment's materials when all vents are closed. The breathability of this product may be better when the vents can be opened. This garment has a removable water-resistant liner. The breathability rating above was achieved with the thermal and water-resistant liners removed. When tested with the water-resistant liner installed, the breathability rating reduced but remained within half a star.


Jacket and Pants - Crash Impact Risk Zones


This diagram is a pictorial representation of the crash impact risk Zones.



Zone 1

 High risk of abrasion
 High risk of impact

Zone 2

 High risk of abrasion

Zone 3

 Medium risk of abrasion

Zone 4

 Low risk of abrasion

Removable liners

| | |
|-----------------------|-------------------------------------|
| Thermal liner | <input checked="" type="checkbox"/> |
| Water resistant liner | <input checked="" type="checkbox"/> |

Removable impact protection

| | Pockets | Armour |
|----------|-------------------------------------|-------------------------------------|
| Elbow | <input checked="" type="checkbox"/> | <input checked="" type="checkbox"/> |
| Shoulder | <input checked="" type="checkbox"/> | <input checked="" type="checkbox"/> |
| Back | <input checked="" type="checkbox"/> | <input type="checkbox"/> |

Abrasion Resistance

The jacket was tested for abrasion resistance in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table below. The colour coding is based on the worst performing material in each zone.



Abrasion Resistance Performance

| | |
|-----------------|------|
| Abrasion rating | 2/10 |
| Abrasion score | 1.40 |

| Determining Criteria | Area | Good | Acceptable | Marginal | Poor |
|----------------------|------------|-------|------------|-----------|-------|
| High abrasion risk | Zone 1 & 2 | > 5.6 | 3.0 - 5.6 | 1.3 - 2.9 | < 1.3 |
| Medium abrasion risk | Zone 3 | > 2.5 | 1.8 - 2.5 | 0.8 - 1.7 | < 0.8 |
| Low abrasion risk | Zone 4 | >1.5 | 1.0 - 1.5 | 0.4 - 0.9 | < 0.4 |

Individual Abrasion Resistance Results: - The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone. Abrasion times are capped at a maximum of 10.00s.

Abrasion time for each test (seconds)

| Zone | Coverage (%) | Sample 1 | Sample 2 | Sample 3 | Sample 4 | Sample 5 | Sample 6 | Average | Grade | |
|------------|--------------|----------|----------|----------|----------|----------|----------|---------|-------|---|
| Zone 1 & 2 | Material A | 100% | 2.49 | 2.86 | 1.03 | 2.62 | 2.54 | 1.29 | 2.14 | M |
| | Material B | 100% | 0.25 | 0.22 | 0.39 | 0.23 | 0.21 | 0.39 | 0.28 | P |
| Zone 3 | Material A | 100% | 0.25 | 0.22 | 0.39 | 0.23 | 0.21 | 0.39 | 0.28 | P |
| | Material B | 100% | 0.25 | 0.22 | 0.39 | 0.23 | 0.21 | 0.39 | 0.28 | P |
| Zone 4 | Material A | 100% | 0.25 | 0.22 | 0.39 | 0.23 | 0.21 | 0.39 | 0.28 | P |
| | Material B | 100% | 0.25 | 0.22 | 0.39 | 0.23 | 0.21 | 0.39 | 0.28 | P |

Details of materials used in jacket

| | |
|------------|--|
| Material A | Coarse woven fabric shell, foam layer and fabric inner liner |
| Material B | Woven fabric shell, foam layer and fabric inner liner |

Burst Strength

The jacket was tested for burst strength in accordance with MotoCAP test protocols. The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table below.



Burst Strength Performance

| | |
|--------------|------|
| Burst rating | 9/10 |
| Burst score | 999 |

| Determining Criteria | Unit | Good | Acceptable | Marginal | Poor |
|----------------------|-------|--------|------------|-----------|-------|
| Burst strength | (kPa) | > 1000 | 800 - 1000 | 500 - 799 | < 500 |

Individual Burst Strength Results: - The table below shows the burst pressure in kilopascals (kPA) for each sample tested by Zone and the average result for each zone.

Burst pressure for each seam (kPA)

| Area | Sample 1 | Sample 2 | Sample 3 | Sample 4 | Sample 5 | Sample 6 | Average | |
|-------------|----------|----------|----------|----------|----------|----------|---------|---|
| Zones 1 & 2 | 735 | 350 | 1871 | 719 | 1424 | 1136 | 1039 | G |
| Zones 3 & 4 | 1118 | 746 | 959 | 675 | 734 | 788 | 836 | A |

Impact Protection

The jacket was tested for impact protection and coverage in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table below. The colour coding is based on the worst performing score for average or maximum force for each impact zone. Areas shaded black are not considered for impact protection ratings.



Impact Protection Performance

| | |
|---------------|------|
| Impact rating | 2/10 |
| Impact score | 12.0 |

| Determining Criteria | Unit | Good | Acceptable | Marginal | Poor* |
|----------------------|------|------|------------|----------|-------|
| Impact force | (kN) | < 15 | 15 - 24 | 25 - 30 | > 30 |

* Poor may also indicate that no impact protector, or impact protector pocket is present in the garment

Individual Impact Protector Results: - The table below shows the test results for each strike on each impact protector in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone. Individual strike results are capped at a maximum of 50kN.

| Impact protector type | Elbow | | Shoulder | |
|-------------------------------------|-------|---|----------|---|
| Average force (kN) | 34.9 | P | 34.9 | P |
| Maximum force (kN) | 40.6 | P | 40.6 | P |
| Coverage of Zone 1 area | 120% | | 130% | |
| Coverage of Zone after displacement | 100% | | 100% | |

Individual Impact Protector Results: - The table below shows the test results for each strike on individual impact protectors in kilonewtons (kN) and the position of the strike. Individual strike results are capped at a maximum of 50kN.

Force transfer for each impact strike (kN)

| Impact protector type | Elbow | | | Shoulder | | |
|-----------------------|--------|------|------|----------|------|------|
| | Centre | Mid | Edge | Centre | Mid | Edge |
| Impact Protector 1 | 26.8 | 33.4 | 36.8 | 26.8 | 33.4 | 36.8 |
| Impact Protector 2 | 39.1 | 37.7 | 40.6 | 39.1 | 37.7 | 40.6 |
| Impact Protector 3 | 30.7 | 31.8 | 36.9 | 30.7 | 31.8 | 36.9 |

Breathability

The jacket was tested for breathability following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

| Without removable liners | | With water-resistant liner | |
|--------------------------|-------|----------------------------|-------|
| Breathability rating | ↘ | Breathability rating | ↘ |
| Breathability score | 0.042 | Breathability score | 0.015 |

| Moisture Vapour Resistance - R_{et} (kPa.m ² /W) | 1 | 2 | Average |
|---|--------|--------|---------|
| Without removable liners | 444.1 | 521.7 | 482.9 |
| With water-resistant liner | 1781.9 | 1585.7 | 1683.8 |

| Thermal Resistance - R_{ct} (K.m ² /W) | 1 | 2 | Average |
|---|-------|-------|---------|
| Without removable liners | 0.341 | 0.342 | 0.341 |
| With water-resistant liner | 0.423 | 0.431 | 0.427 |

Water spray and rain resistance

This jacket is advertised as water-resistant, and so has been tested for water spray and rain resistance according to the MotoCAP test protocols. The table below shows the water absorbed (ml) and the wetting proportion (%) of the garment and undergarments due to water absorption.

| | Water absorbed by garment | | Water absorbed by underwear | |
|----------------|---------------------------|----------------|-----------------------------|----------------|
| | Volume (ml) | Percentage (%) | Volume (ml) | Percentage (%) |
| Jacket 1 | 452 | 25% | 145 | 49% |
| Jacket 2 | 384 | 21% | 69 | 24% |
| Average | 418 | 23% | 107 | 36% |

Location of wetting

There was minor wetting to the cotton underwear present at the chest and major wetting at the back for one jacket and major wetting at the chest of the other jacket tested.

Assessment Details.

| | |
|------------------------|----------------------------|
| Brand | 1Tonne |
| Model | Explorer All Season Ladies |
| Type | Jacket - Textile |
| Date purchased | 22 May 2023 |
| Tested by | AMCAF, Deakin University |
| Report approved by | MotoCAP Chief Scientist |
| Garment test reference | J23T24 |
| Rating first published | July 2023 |
| Rating updated | 28 July 2023 |