



This MotoCAP safety rating applies to:

Brand X-treme Model Eva

Type Jacket - Textile


Date purchased 1 June 2023
Sizes tested L and XL
Test garment gender Female
Style All Purpose
RRP \$169.00

Test Results Summary	Rating	Score
MotoCAP Protection Rating	+	11.9
Abrasion	1/10	0.42
Burst	9/10	977
Impact	1/10	0.0
MotoCAP Breathability Rating	+	0.012
Moisture Vapour Resistance	-	1493.9
Thermal Resistance	-	0.309
Water resistance	1/10	39.4

This garment is fitted with impact protectors for the elbows, shoulders and back. Replacing the elbow and shoulder armour with higher performing impact protectors would improve the protection levels of this garment. There are zipped vents in the chest and back to allow controlled airflow movement through the garment. The breathability rating is based on tests of the garment's materials when all vents are closed. The breathability of this product may be better when the vents can be opened. Breathability was measured without the removable thermal liner installed.

Jacket and Pants - Crash Impact Risk Zones

This diagram is a pictorial representation of the crash impact risk Zones.





Abrasion Resistance

The jacket was tested for abrasion resistance in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table below. The colour coding is based on the worst performing material in each zone.



Abrasion Resistance Performance

Abrasion rating	1/10
Abrasion score	0.42

Determining Criteria	Area	Good	Acceptable	Marginal	Poor
High abrasion risk	Zone 1 & 2	> 5.6	3.0 - 5.6	1.3 - 2.9	< 1.3
Medium abrasion risk	Zone 3	> 2.5	1.8 - 2.5	0.8 - 1.7	< 0.8
Low abrasion risk	Zone 4	>1.5	1.0 - 1.5	0.4 - 0.9	< 0.4

Individual Abrasion Resistance Results: - The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone. Abrasion times are capped at a maximum of 10.00s.

Abrasion time for each test (seconds)

Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average
100%	0.43	0.41	0.39	0.40	0.32	0.59	0.42
Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average
100%	0.43	0.41	0.39	0.40	0.32	0.59	0.42
Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average
100%	0.43	0.41	0.39	0.40	0.32	0.59	0.42
	100% Coverage (%) 100% Coverage (%)	100% 0.43 Coverage (%) Sample 1 100% 0.43 Coverage (%) Sample 1	100% 0.43 0.41 Coverage (%) Sample 1 Sample 2 100% 0.43 0.41 Coverage (%) Sample 1 Sample 2	100% 0.43 0.41 0.39 Coverage (%) Sample 1 Sample 2 Sample 3 100% 0.43 0.41 0.39 Coverage (%) Sample 1 Sample 2 Sample 3	100% 0.43 0.41 0.39 0.40 Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 100% 0.43 0.41 0.39 0.40 Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4	100% 0.43 0.41 0.39 0.40 0.32 Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 Sample 5 100% 0.43 0.41 0.39 0.40 0.32 Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 Sample 5	100% 0.43 0.41 0.39 0.40 0.32 0.59 Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 Sample 5 Sample 6 100% 0.43 0.41 0.39 0.40 0.32 0.59 Coverage (%) Sample 1 Sample 2 Sample 3 Sample 4 Sample 5 Sample 6

Details of materials used in jacket

Material A Woven fabric shell, water-resistant layer and mesh inner liner



Burst Strength

The jacket was tested for burst strength in accordance with MotoCAP test protocols. The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table below.



Burst Strength Performance	Burst	Strength	Performance
-----------------------------------	-------	----------	-------------

Burst rating	9/10
Burst score	977

Determining Criteria	Unit	Good	Acceptable	Marginal	Poor
Burst strength	(kPa)	> 1000	800 - 1000	500 - 799	< 500

Individual Burst Strength Results: - The table below shows the burst pressure in kilopascals (kPA) for each sample tested by Zone and the average result for each zone.

Burst pressure for each seam (kPA)

Area	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Zones 1 & 2	977	1063	994	1063	1088	973	1026	G
Zones 3 & 4	1143	562	634	871	689	789	781	M



Impact Protection

The jacket was tested for impact protection and coverage in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table below. The colour coding is based on the worst performing score for average or maximum force for each impact zone. Areas shaded black are not considered for impact protection ratings.



Impact Protection Performance

Impact rating	1/10
Impact score	0.0

Determining Criteria	Unit	Good	Acceptable	Marginal	Poor*
Impact force	(kN)	< 15	15 - 24	25 - 30	> 30

^{*} Poor may also indicate that no impact protector, or impact protector pocket is present in the garment

Individual Impact Protector Results: - The table below shows the test results for each strike on each impact protector in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone. Individual strike results are capped at a maximum of 50kN.

Impact protector type	Elbow	Shoulder
Average force (kN)	49.8 P	47.8 P
Maximum force (kN)	50.0 P	49.5 P
Coverage of Zone 1 area	125%	125%
Coverage of Zone after displacement	100%	100%

Individual Impact Protector Results: - The table below shows the test results for each strike on individual impact protectors in kilonewtons (kN) and the position of the strike. Individual strike results are capped at a maximum of 50kN.

Force transfer for each impact strike (kN)

Impact protector type	Elbow Shoulder					
Strike location	Centre	Mid	Edge	Centre	Mid	Edge
Impact Protector 1	50.0	49.6	49.0	47.3	49.1	47.2
Impact Protector 2	50.0	50.0	50.0	49.5	47.3	46.6
Impact Protector 3	50.0	49.3	50.0	46.5	49.2	47.8



Breathability

The jacket was tested for breathability following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

Without removable I	iners	With water-resistant liner		
Breathability rating		Brea	thability rating	N/A
Breathability score	0.012	Breathability score N/A		
Moisture Vapour Resi	stance - R _{et} (kPa.m²/W)	1	2	Average
Without removable liner	S	1568.9	1418.9	1493.9
With water-resistant line	er	N/A	N/A	N/A
Thermal Resistance -	R _{ct} (K.m²/W)	1	2	Average
Without removable liner	S	0.310	0.308	0.309
With water-resistant line	er	N/A	N/A	N/A

Water spray and rain resistance

This jacket is advertised as water-resistant, and so has been tested for water spray and rain resistance according to the MotoCAP test protocols. The table below shows the water absorbed (ml) and the wetting proportion (%) of the garment and undergarments due to water absorption.

	Water absorbe	ed by garment	Water absorbed by underwear		
	Volume (ml)	Percentage (%)	Volume (ml)	Percentage (%)	
Jacket 1	237	20%	108	36%	
Jacket 2	216	18%	127	43%	
Average	226	19%	117	39%	

Location of wetting

There was major wetting to the cotton underwear present at the cuffs of the sleeves and chest for both jackets tested.

Assessment Details.

Brand X-treme Model Eva

Type Jacket - Textile
Date purchased 1 June 2023

Tested by AMCAF, Deakin University Report approved by MotoCAP Chief Scientist

Garment test reference J23T29
Rating first published July 2023
Rating updated 28 July 2023