


This MotoCAP safety rating applies to:


Brand	Merlin
Model	Wishaw Vented
Type	Jacket - Leather
Date purchased	22 November 2023
Sizes tested	XL and XL
Test garment gender	Male
Style	All Purpose
RRP	\$698.95


Test Results Summary	Rating	Score
MotoCAP Protection Rating	★★★★	59.2
Abrasion	7/10	5.44
Burst	10/10	1458
Impact	8/10	58.0
MotoCAP Breathability Rating	★★	0.297
Moisture Vapour Resistance	-	49.9
Thermal Resistance	-	0.247
Water resistance	N/A	N/A


This garment is fitted with impact protectors for the elbows, shoulders and back. Perforated leather is located in the arms and zipped vents in the chest and back allow controlled airflow movement through the garment. The breathability rating is based on tests of the garment's materials with all vents closed. The breathability of this product may be better with the vents opened. Breathability was measured without the removable thermal liner installed. There is the potential for burns from heat transferred through the metal snap fasteners on the wrist during a slide.


Jacket and Pants - Crash Impact Risk Zones


This diagram is a pictorial representation of the crash impact risk Zones.



Zone 1

 High risk of abrasion
 High risk of impact

Zone 2

 High risk of abrasion

Zone 3

 Medium risk of abrasion

Zone 4

 Low risk of abrasion

Removable liners

Thermal liner	<input checked="" type="checkbox"/>
Water-resistant liner	<input type="checkbox"/>

Removable impact protection

	Pockets	Armour
Elbow	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>
Shoulder	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>
Back	<input checked="" type="checkbox"/>	<input type="checkbox"/>

Abrasion Resistance

The jacket was tested for abrasion resistance in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table below. The colour coding is based on the worst performing material in each zone.



Abrasion Resistance Performance

Abrasion rating	7/10
Abrasion score	5.44

Determining Criteria	Area	Good	Acceptable	Marginal	Poor
High abrasion risk	Zones 1 & 2	> 5.6	3.0 - 5.6	1.3 - 2.9	< 1.3
Medium abrasion risk	Zone 3	> 2.5	1.8 - 2.5	0.8 - 1.7	< 0.8
Low abrasion risk	Zone 4	>1.5	1.0 - 1.5	0.4 - 0.9	< 0.4

Individual Abrasion Resistance Results: - The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone. Abrasion times are capped at a maximum of 10.00s.

Abrasion time for each test (seconds)

Zones 1 & 2	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Material A	38%	7.06	6.87	6.77	6.13	4.85	10.33	7.00	G
Material B	62%	4.09	4.45	3.05	5.29	7.25	6.69	5.14	A
Zone 3	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Material A	15%	7.06	6.87	6.77	6.13	4.85	10.33	7.00	G
Material C	85%	4.46	6.78	4.15	4.06	2.93	3.48	4.31	G
Zone 4	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Material B	90%	4.09	4.45	3.05	5.29	7.25	6.69	5.14	G
Material C	10%	4.45	6.78	4.15	4.06	2.93	3.48	4.31	G

Details of materials used in jacket

Material A	Quilted leather shell, foam layer and fabric inner liner
Material B	Leather shell, foam layer and fabric inner liner
Material C	Perforated leather shell, foam layer and fabric inner liner

Burst Strength

The jacket was tested for burst strength in accordance with MotoCAP test protocols. The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table below.



Burst Strength Performance

Burst rating	10/10
Burst score	1458

Determining Criteria	Unit	Good	Acceptable	Marginal	Poor
Burst strength	(kPa)	> 1000	800 - 1000	500 - 799	< 500

Individual Burst Strength Results: - The table below shows the burst pressure in kilopascals (kPA) for each sample tested by Zone and the average result for each zone.

Burst pressure for each seam (kPA)

Area	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Zones 1 & 2	1701	1632	1667	1309	1283	1549	1524	G
Zones 3 & 4	980	800	1886	1694	1022	799	1197	G

Impact Protection

The jacket was tested for impact protection and coverage in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table below. The colour coding is based on the worst performing score for average or maximum force for each impact zone. Areas shaded black are not considered for impact protection ratings.



Impact Protection Performance

Impact rating 8/10
Impact score 58.0

Determining Criteria	Unit	Good	Acceptable	Marginal	Poor*
Impact force	(kN)	< 15	15 - 24	25 - 30	> 30

* Poor may also indicate that no impact protector, or impact protector pocket is present in the garment

Impact Protector Results: - The table below shows the average and maximum force transmitted through each impact protector type in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone.

Impact protector type	Elbow		Shoulder	
Average force (kN)	13.6	G	13.1	G
Maximum force (kN)	17.6	A	14.9	G
Coverage of Zone 1 area	115%		105%	
Coverage of Zone after displacement	90%		100%	

Individual Impact Protector Results: - The table below shows the test results for each strike on individual impact protectors in kilonewtons (kN) and the position of the strike. Individual strike results are capped at a maximum of 50kN.

Force transfer for each impact strike (kN)

Impact protector type	Elbow			Shoulder		
	Centre	Mid	Edge	Centre	Mid	Edge
Impact Protector 1	11.3	14.4	17.6	12.3	13.3	14.9
Impact Protector 2	10.2	13.6	14.9	12.3	13.2	14.5
Impact Protector 3	11.5	12.8	16.3	12.0	12.1	13.1

Breathability

The jacket was tested for breathability following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

Without removable liners		With water-resistant liner	
Breathability rating	★★	Breathability rating	N/A
Breathability score	0.297	Breathability score	N/A

Moisture Vapour Resistance - R_{et} (kPa.m ² /W)	1	2	Average
Without removable liners	50.9	48.9	49.9
With water-resistant liner	N/A	N/A	N/A
Thermal Resistance - R_{ct} (K.m ² /W)	1	2	Average
Without removable liners	0.243	0.252	0.247
With water-resistant liner	N/A	N/A	N/A

Water spray and rain resistance

This jacket has not been advertised as water-resistant so has not been tested for water spray and rain resistance.

Assessment Details.

Brand	Merlin
Model	Wishaw Vented
Type	Jacket - Leather
Date purchased	22 November 2023
Tested by	AMCAF, Deakin University
Report approved by	MotoCAP Chief Scientist
Garment test reference	J24L06
Rating first published	January 2024
Rating updated	10 January 2024