



# This MotoCAP safety rating applies to:

Brand BMW


Model GS Rallye GTX
Type Jacket - Textile
Date purchased 26 May 2025
Sizes tested 56 and 58
Test garment gender Male
Style Adventure
RRP \$1,590.00

Test Results Summary	Rating	Score
MotoCAP Protection Rating	**	34.9
Abrasion	1/10	0.77
Burst	10/10	1354
Impact	8/10	58.3
MotoCAP Breathability Rating	***	0.545
Moisture Vapour Resistance	-	26.6
Thermal Resistance	-	0.242
Water resistance	7/10	5.9

This garment is fitted with impact protectors for the elbows, shoulders and back. There are zipped vents in the chest, sides, arms and back to allow controlled airflow movement through the garment. The breathability rating is based on tests of the garment's materials when all vents are closed. The breathability of this product may be better when the vents are opened. This garment has a removable water-resistant liner. The breathability rating above was achieved with the water-resistant liner removed. When tested with the water-resistant liner installed, the breathability rating reduced to 1 star.

### **Jacket and Pants - Crash Impact Risk Zones**

This diagram is a pictorial representation of the crash impact risk Zones.





### **Abrasion Resistance**

The jacket was tested for abrasion resistance in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table below. The colour coding is based on the worst performing material in each zone.



### **Abrasion Resistance Performance**

Abrasion rating	1/10
Abrasion score	0.77

<b>Determining Criteria</b>	Area	Good	Acceptable	Marginal	Poor
High abrasion risk	Zone 1 & 2	> 5.6	3.0 - 5.6	1.3 - 2.9	< 1.3
Medium abrasion risk	Zone 3	> 2.5	1.8 - 2.5	0.8 - 1.7	< 0.8
Low abrasion risk	Zone 4	>1.5	1.0 - 1.5	0.4 - 0.9	< 0.4

**Individual Abrasion Resistance Results:** - The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone. Abrasion times are capped at a maximum of 10.00s.

### Abrasion time for each test (seconds)

ADIASION UNIO	ioi eacii lest (se	conus						
Zone 1 & 2	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average
Material A	100%	0.90	0.73	0.88	0.77	0.67	0.68	0.77
Zone 3	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average
Material A	100%	0.90	0.73	0.88	0.77	0.67	0.68	0.77
Zone 4	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average
Material A	100%	0.90	0.73	0.88	0.77	0.67	0.68	0.77

### Details of materials used in jacket

Material A Woven fabric shell with mesh inner liner



## **Burst Strength**

The jacket was tested for burst strength in accordance with MotoCAP test protocols. The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table below.



<b>Burst Strength Performance</b>					
Burst rating	10/10				
Burst score	1354				

<b>Determining Criteria</b>	Unit	Good	Acceptable	Marginal	Poor
Burst strength	(kPa)	> 1000	800 - 1000	500 - 799	< 500

**Individual Burst Strength Results:** - The table below shows the burst pressure in kilopascals (kPA) for each sample tested by Zone and the average result for each zone.

# Burst pressure for each seam (kPA)

Area	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Zones 1 & 2	1519	1539	1337	1196	1287	1243	1353	G
Zones 3 & 4	1297	1612	1078	1033	1655	1470	1358	G



## **Impact Protection**

The jacket was tested for impact protection and coverage in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table below. The colour coding is based on the worst performing score for average or maximum force for each impact zone. Areas shaded black are not considered for impact protection ratings.



Impact Protect	ion Performance
Impact rating	8/10
Impact score	58.3

<b>Determining Criteria</b>	Unit	Good	Acceptable	Marginal	Poor*
Impact force	(kN)	< 15	15 - 24	25 - 30	> 30

<sup>\*</sup> Poor may also indicate that no impact protector, or impact protector pocket is present in the garment

**Individual Impact Protector Results:** - The table below shows the test results for each strike on each impact protector in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone. Individual strike results are capped at a maximum of 50kN.

Impact protector type	Elbow		Shoulder
Average force (kN)	11.6	G	12.8 <b>G</b>
Maximum force (kN)	20.0	A	22.1 A
Coverage of Zone 1 area	120%	<del></del>	110%
Coverage of Zone after displacement	100%		100%

**Individual Impact Protector Results:** - The table below shows the test results for each strike on individual impact protectors in kilonewtons (kN) and the position of the strike. Individual strike results are capped at a maximum of 50kN.

### Force transfer for each impact strike (kN)

Impact protector type	Elbow	Shoulder				
Strike location	Centre	Mid	Edge	Centre	Mid	Edge
Impact Protector 1	8.0	14.1	13.0	10.3	10.5	22.1
Impact Protector 2	7.0	10.0	20.0	11.0	11.7	16.3
Impact Protector 3	7.3	8.5	36.5	10.2	13.2	10.2



## **Breathability**

The jacket was tested for breathability following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

Without removable	With water-resistant liner				
Breathability rating	Brea	thability rating	*		
Breathability score	0.545	Breathability score		0.226	
Moisture Vapour Resi	stance - R <sub>et</sub> (kPa.m²/W)	1	2	Average	
Without removable lines	°S	26.2	27.1	26.6	
With water-resistant line	er	89.3	91.6	90.4	
Thermal Resistance -	R <sub>ct</sub> (K.m²/W)	1	2	Average	
Without removable lines	rs .	0.244	0.240	0.242	
With water-resistant line	er	0.345	0.338	0.341	

# Water spray and rain resistance

This jacket is advertised as water-resistant, and so has been tested for water spray and rain resistance according to the MotoCAP test protocols. The table below shows the water absorbed (ml) and the wetting proportion (%) of the garment and undergarments due to water absorption.

	Water absorbed by garment		Water absorbed by underwear			
	Volume (ml)	Percentage (%)	Volume (ml)	Percentage (%)	Water Resistar	nce
Jacket 1	83	4%	36	12%	Performance	
Jacket 2	112	5%	0	0%	Water rating	7/10
Average	97	4%	18	6%	Water Score	5.93

# **Location of wetting**

There was minor wetting to the cotton underwear present at the neck and chest for both jackets tested.

Assessment Details.	
Brand	BMW
Model	GS Rallye GTX
Туре	Jacket - Textile
Date purchased	26 May 2025
Tested by	AMCAF, Deakin University
Report approved by	MotoCAP Chief Scientist
Garment test reference	J25T34
Rating first published	August 2025
Rating updated	13 August 2025